



# Base Oil

Productinformation Article no. 299 - 304

06.12.2017

Kreidezeit Base Oil is a classic, resin-free half oil, consisting of 50% linseed oil varnish and 50% natural balsamic turpentine. Half oil has been proven for centuries as an ideal primer for subsequent coats of oil paint for both interiors and exteriors.

Suitable for use as a primer for subsequent coats with:

- opaque Stand Oil Paints on all untreated wood
- pigmented Wood Lazure on highly absorbent or weathered wood

Also suitable as a single treatment for low-stress indoor surfaces » classic oiled (linseed oil) surfaces: furniture, beams, cladding and much more.

Contains natural balsamic turpentine, making the Base Oil perfect for all wooden surfaces and types of wood, even for dense wood and wood containing tannin.

The high linseed oil content ensures that the product deeply penetrates into the tiniest of pores thanks to the small size of the molecules. This ensures that the subsequent oil paint coats stick well to the substrate.

Kreidezeit Base Oil consists exclusively of natural oils. It contains no 'hidden' alkyd resins produced from non-drying oils such as rapeseed, soybean or sunflower oil.

## ■ Properties

- Dirt and water repellent
- Resin-free, solvent-based
- Oil paint sticks well to the substrate as a result
- Doesn't tear or become brittle
- Diffusible, antistatic and warm to touch
- Transparent, honey-toned and colour-deepening
- Excellent penetration
- Easy to work with and touch up
- Saliva and sweat-resistant according to DIN 53160
- Cobalt, lead and barium-free
- Vegan

## ■ Composition (full declaration)

Linseed oil, balsamic turpentine, linseed stand oil and manganese drier.

## ■ Suitable tools

- Paint brush / flat brush
- Short-pile roller (Magic felt, article no. 6517).
- Lint-free cloth, solvent-resistant synthetic sponges

## ■ Test surface

**It is recommended to test the product on an inconspicuous surface before extensive application in order to determine whether the substrate may change colour or react with the product.**

## ■ Substrate requirements

The substrate must be untreated, dust-free, clean, dry, non-greasy, chemically neutral and **absorbent**. The minimum temperature for application is 10°C. Wood moisture content < 15%. **Do not use on damp wood!**

## ■ Preparing the substrate / initial sanding

Remove any resin pockets and old synthetic resin-based coats. For outdoor use: soak any absorbent cutting edges and end grain areas with Kreidezeit Resin Oil (article no. 341) and allow to dry for at least 24 hours.

Sand down new or weathered wood (grit P80-100), rounding the edges. Do not use a finer sandpaper as this will make the wood too dense and unable to absorb enough oil. New, smooth, planed or finely pre-sanded wood should be rough sanded to ensure the oil can be absorbed. Dust down thoroughly after sanding.

## ■ Application

Shake product briefly before application. Apply one or two coats of Kreidezeit Base Oil, allowing the first coat to dry before applying the second. The substrate may require sanding before applying the second coat.

If using containers with different batch numbers, mix and stir together prior to application. The product must not be poured onto surfaces!

Clean and dust down untreated substrates.

Kreidezeit Base Oil is ready for application undiluted.

**Please note:** wood in outdoor areas should be fitted with non-rusting metal screws and fittings, otherwise dark stains may appear after applying oil.

Processing and drying temperatures:

At least 10°C for a minimum of 48 hours.

### 1. First coat

Apply Kreidezeit Base Oil evenly with a brush, short-pile roller, cloth or sponge. After 10-20 minutes, **thoroughly wipe** the entire treated area with a dry, lint-free cloth until the surface has a uniform satin appearance.

**Ensure that all unabsorbed oil has been completely removed**, as otherwise shiny or sticky patches may remain. Kreidezeit Base Oil must fully penetrate into the wood. **It must not form a layer on the wood.**

### 2. Re-sanding between coats (optional)

Re-sanding between coats is only required if the surface has dried rough, for example if wood fibres have dried proud of the surface. Use sand paper (grit P100-120) in the direction of the fibre.

Dust down thoroughly after sanding.



# Base Oil

Productinformation Article no. 299 - 304

06.12.2017

### 3. Second coat (optional)

A second coat is required if the product is applied indoors on its own or if subsequently using Stand Oil Paint on highly absorbent or weathered wood. Repeat as per the first coat.

### 4. Subsequent coats

If applying subsequent coats, please see the product information on Stand Oil Paint or Wood Lazure.

### 5. Wax treatment

Oiled surfaces generally do not require wax treatment. To improve the gloss, you can finish with Kreidezeit Carnauba Wax Emulsion (article no. 420) after at least 48 hours. To do this, dilute 1 part emulsion with 1 part water. Apply evenly and thinly, allow to dry and polish as needed.

#### ■ Tinting

This product can be tinted with any Kreidezeit Pigment. See our 'Pigments in Oil' colour chart for examples. Start by stirring the pigments into a small amount of the product until it forms a lump-free paste, and then stir into the main mixture. The pigments can be mixed freely with each other. Colour samples are available from our retailers. Alternatively, the product can be tinted in any ratio with Stand Oil Paint, half rich (article no. D1100-1115).

#### ■ Dilution

The product is applied undiluted, but can be diluted as necessary with Balsamic Turpentine (article no. 447).

#### ■ Drying time

Dry and re-coatable at 20°C and 60% relative humidity after approx. 24 hours (48 hours for substrates containing tannin, e.g. oak, etc.).

High humidity, cold temperatures and substrates containing tannin significantly extend the drying time.

Hardened after approx. 4 weeks. Use the surface gently and protect from water during this time.

#### ■ Cleaning the tools

Clean immediately after use with Balsamic Turpentine (article no. 447) and then with Marseille Soap (article no. 223) or Corfu Soap (article no. 226).

#### ■ Application rate

Depending on the absorption of the substrate, approx. 0.07 - 0.10 litres per m<sup>2</sup> per coat.

Exact consumption rate to be determined on the actual substrate.

#### ■ Container sizes

Article no. 299 0.375 l

Article no. 300 0.75 l

Article no. 301 2.5 l

Article no. 302 5 l

Article no. 303 10 l

Article no. 304 20 l

For prices, please refer to the valid price list.

#### ■ Storage

The product will keep for at least 2 years if stored airtight and protected from frost.

#### ■ Disposing leftover product

Do not dispose of the product remains in wastewater, but keep hermetically sealed for later use. Dried product remains can be disposed of with household waste. Empty containers can be recycled.

Please adhere to current statutory regulations for disposing of paint and paint residues.

#### ■ Notes

Due to the content of natural oils, a yellowing occurs on surfaces with low exposure to light. A typical odour is emitted when natural oils dry; this disappears with time. Failure to remove iron filings on the surface can cause discolouration when applying the product. Not recommended for use inside cupboards; these are best left untreated or can be treated with Carnauba Wax Emulsion (article no. 420), Marseille Soap (article no. 223) or Corfu Soap (article no. 226).

#### ■ EU VOC Value acc. to 2004/42/EC

VOC limit / Max. VOC content (cat. A/f): 700 g/l (2010),

Product contains max. 490 g/l VOC.

#### ■ Warning

Ensure that work materials that have been soaked with the product, such as cloths and sponges, sanding dust or polishing pads with undried oil, are securely stored sealed in metal containers or in water. Avoid any contact of the oil with porous insulation; otherwise, there is a **risk of self-ignition** due to the vegetable oil content. The product itself is not self-igniting. Do not pour the product onto surfaces.

Please check for allergies to natural substances. **Keep out of reach of children!**



## ■ Hazard Statements

- H226: Flammable liquid and vapour.
- H302: Harmful if swallowed.
- H304: May be fatal if swallowed and enters airways.
- H312: Harmful in contact with skin.
- H315: Causes skin irritation.
- H319: Causes serious eye irritation.
- H332: Harmful if inhaled.
- H411: Toxic to aquatic life with long lasting effects.
- EUH 208: Contains balsamic turpentine. May produce an allergic reaction.

## ■ Precautionary Statements

- P261: Avoid breathing vapours/spray.
- P280: Wear protective gloves/protective clothing/eye protection/face protection.
- P312: Call a POISON CENTER or doctor/physician if you feel unwell.
- P331: Do NOT induce vomiting.
- P301 + P310: IF SWALLOWED: Immediately call a POISON CENTER or doctor/physician.
- P303 + P361 + P353: IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin.
- P305 + P351 + P338: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
- P333 + P313: If skin irritation or rash occurs: Get medical advice/attention.
- P405: Store locked up.
- P501: Dispose of contents/container to special disposal.

*The information above was determined based on our most recent experiences. Due to processing methods and environmental influences, as well as the varying nature of the substrates, liability for the general validity of the individual recommendations is excluded. Users must test the product prior to application to ensure it is fit for the designated purpose (sample coating). This document is no longer valid if a new version is published or the product is modified.  
For the latest product information, please contact Kreidezeit directly or visit our website at [www.kreidezeit.de](http://www.kreidezeit.de)*