



Hard Oil light solvent-free

Product information Article no. 4207

19.06.2025

With KREIDEZEIT Hard Oil light it is possible to preserve the natural raw wood look of untreated wood and to optimally protect the surface from dirt and water.

KREIDEZEIT Hard Oil light is a hard-wearing protection for many interior surfaces.

KREIDEZEIT Hard Oil light does not contain any solvents or water, and consists exclusively of natural oils and resins. It contains no 'hidden' alkyd resins produced from non-drying oils such as rapeseed, soybean or sunflower oil.

In addition, the use of titanium dioxide has also been deliberately avoided in this product; the whitening effect comes exclusively from the use of zinc sulphide.

■ Properties

- dirt and water-resistant
- Solvent and water-free, very economical
- Doesn't tear or become brittle
- Diffusible, antistatic and warm to touch
- Transparent
- Excellent penetration
- Easy to work with and touch up
- Saliva and sweat-resistant according to DIN 53160
- Cobalt, lead and barium-free
- Vegan

■ Composition (full declaration)

Linseed oil, linseed stand oil, tung stand oil, castor stand oil, glycerol ester of wood rosin, carnauba wax, zinc sulphide, manganese drier.

■ Suitable tools

- Paint brush / flat brush
- Short-pile roller (Magic felt, article no. 9216).
- Lint-free cloth, solvent-resistant synthetic sponges
- For larger areas: Floor machines with soft pads

Do not apply product with surface/ground scraper.

■ Test surface

It is recommended to test the product on an inconspicuous surface before extensive application in order to determine whether the substrate may change colour or react with the product.

■ Substrate requirements

The substrate must be untreated, dust-free, clean, dry, non-greasy, chemically neutral and **absorbent**. The minimum temperature for application is 10 °C. Wood moisture content < 15%.

■ Application

Stir the product before use. Apply two coats of KREIDEZEIT Hard Oil light, allowing the first coat to dry before applying the second. The substrate may require sanding before applying the second coat. It is recommended to dilute the product with at least 20% Balsamic Turpentine (article no. 4301) for the first coat on very dense, poorly absorbent and tannin-rich wood (such as oak).

If using containers with different batch numbers, mix and stir together prior to application. The product must not be poured onto surfaces!

Clean and dust down untreated substrates.

1. Initial sanding

Sand the wood (grit P80-100), rounding the edges. Do not use a finer sandpaper as this will make the wood too dense and unable to absorb enough oil.

New, smooth, planed or finely pre-sanded wood should be rough sanded to ensure the oil can be absorbed.

Dust down thoroughly after sanding.

2. First coat

a) Manual application:

Apply KREIDEZEIT Hard Oil light evenly with a brush, short-pile roller, cloth or sponge. After 10-20 minutes, **thoroughly wipe** the entire treated area with a dry, lint-free cloth until the surface has a uniform satin appearance.

b) Machine application:

Apply KREIDEZEIT Hard Oil light with a short-pile roller. After 10-20 minutes, **thoroughly wipe** the entire treated area with a soft pad until the surface has a uniform satin appearance. Change pad promptly once it becomes saturated.

Ensure that all unabsorbed oil has been completely removed, as otherwise shiny or sticky patches may remain. KREIDEZEIT Hard Oil light **must fully penetrate into the wood. It must not form a layer on the wood.**

3. Re-sanding between coats (optional)

Re-sanding between coats is only required if the surface has dried rough, for example if wood fibres have dried proud of the surface. Use sand paper (grit P180-240) in the direction of the fibre.

Dust down thoroughly after sanding.



Hard Oil light solvent-free

Product information Article no. 4207

19.06.2025

4. Second coat:

Repeat as per the first coat.
Apply the product undiluted.

5. Wax treatment

Oiled surfaces generally do not require wax treatment.
To improve the gloss, you can finish with Kreidezeit Carnauba Wax Emulsion (article no. 5105) after at least 48 hours. To do this, dilute 1 part emulsion with 2 parts water. Apply evenly and thinly, allow to dry and polish as needed.

■ Dilution

The product can be diluted with Balsamic Turpentine (article no. 4301).

■ Drying time

Dry and re-coatable at 20°C and 60% relative humidity after approx. 24 hours (48 hours for substrates containing tannin, e.g. oak, etc.).

High humidity, cold temperatures and substrates containing tannin significantly extend the drying time.

Hardened after approx. 4 weeks. Use the surface gently and protect from water during this time.

■ Maintenance

The surface must be re-oiled as soon as it becomes absorbent again, but no later than when grey spots start to appear. Absorption can be determined by wiping wet. If the surface becomes darker, re-oiling is required. To do this, apply the product again as described above. Very stubborn dirt can be removed beforehand with a scouring pad, abrasive cloth or sand paper (P100).

■ Cleaning, maintenance and handling

- Use surfaces very gently in the first 4 weeks and do not wipe wet.
- Sweep/vacuum with a soft broom or vacuum cleaner with a raised floor brush.
- **Never use hot water** to wipe; use lukewarm water only.
- **Only wipe with a slightly damp cloth!**
- Use a soft cotton floor cloth only.
- **Do not use microfibre cloths/pads** as these will remove the oil.
- **Remove liquid spillages immediately;** do not allow to dry.
- Maintain/restore shine using with Carnauba Wax Emulsion (article no. 5105) in a mopping solution.
- Clean using Olive Care Soap (article no. 5106) or Corfu Soap (article no. 5102) only if needed; use sparingly.

Please see also the fact sheet 'Maintaining and cleaning oiled floors'.

■ Cleaning the tools

Clean immediately after use with Balsamic Turpentine (article no. 4301) and then with Olive Care Soap (article no. 5106) or Corfu Soap (article no. 5102).

■ Application rate

Depending on the absorption of the substrate, approx. 0.05 litres per m² per coat.

Exact consumption rate to be determined on the actual substrate.

■ Container sizes

	Content	Reach
Article no. 4207-375	375 ml	7,5 m ²
Article no. 4207-750	750 ml	15 m ²
Article no. 4207-2.5	2,5 l	50 m ²

For prices, please refer to the valid price list.

■ Storage

The product will keep for at least 2 years if stored airtight and protected from frost.

■ Disposing leftover product

Do not dispose of the product remains in wastewater, but keep hermetically sealed for later use. Dried product remains can be disposed of with household waste. Empty containers can be recycled.

Please adhere to current statutory regulations for disposing of paint and paint residues.

■ Notes

Due to the content of natural oils, a yellowing occurs on surfaces with low exposure to light. A typical odour is emitted when natural oils dry; this disappears with time. Failure to remove iron filings on the surface can cause discolouration when applying the product. Not recommended for use on inside surfaces of cupboards; these are best treated with Shellac Varnish (article no. 8105), Carnauba Wax Emulsion (article no. 5105) or Corfu Soap (article no. 5102).

■ Hazard Classification

Not applicable, no hazardous materials.

■ EU VOC Value acc. to 2004/42/EC

VOC limit / Max. VOC content (cat. A/f): 700 g/l (2010), Product contains max. 30 g/l VOC.



Hard Oil light solvent-free

Productinformation Article no. 4207

19.06.2025

■ Warning

Ensure that work materials that have been soaked with the product, such as cloths and sponges, sanding dust or polishing pads with undried oil, are securely stored sealed in metal containers or in water. Avoid any contact of the oil with porous insulation; otherwise, there is a **risk of self-ignition** due to the vegetable oil content. The product itself is not self-igniting. Do not pour the product onto surfaces. **Keep out of reach of children!** Please check for allergies to natural substances.

The information above was determined based on our most recent experiences. Due to processing methods and environmental influences, as well as the varying nature of the substrates, liability for the general validity of the individual recommendations is excluded. Users must test the product prior to application to ensure it is fit for the designated purpose (sample coating). This document is no longer valid if a new version is published or the product is modified.

For the latest product information, please contact Kreidezeit directly or visit our website at www.kreidezeit.de.